

739 95 Bystřice 1260
Czech Republic

tel.: +420 558 340 011, 558 340 034

fax.: +420 558 340 100

[e-mail: info@jap.cz](mailto:info@jap.cz)

www.jap.cz

IČO: 48398233 VAT: CZ48398233



FeSiMn briquettes

Application:

In metallurgy for steel and iron alloying.

Chemical composition:

Mn	min.	60 %
Si		15 – 19 %
P	max.	0,30 %
S	max.	0,03 %
C	max.	2,5 %

Dimensions of briquettes:

- 55 x 50 x 40 mm
- 75 x 60 x 40 mm

Compressive strength:

8 - 15 MPa

Packing:

- Big-bag.
- In bulk.

Note: Chemical composition can be modified according to customers' requirements.